

RESULT OF ANALYSIS

SiO₂	36.81%
Fe₂O₃	41.21%
Al₂O₃	18.73%
TiO₂	00.18%
MnO	1.28 %
CaO	0.10 %
MgO	01.30%
LOI	00.24%
K₂O	0.04 %
Na₂O	0.02 %

Garnet	99.61%
Quartz	00.10%
Others	0.29 %

Specific Gravity	04.10
Hardness (Moh)	07.30
Chloride	12PPM
T.D.S.	150PPM

GARNET PRO ABRASIVES PTY LTD

ABN 61647205883 ☎ +61 422 868 200

✉ info@garnetpro.com.au 🌐 www.garnetpro.com.au